

- [Home Home](#)
- [About this portal](#)
- [Latest updates](#)

[Resource detail](#)
[Citations](#)

IEC 61249-2-2:2005 Materials for printed boards and other interconnecting structures - Part 2-2: Reinforced base materials, clad and unclad - Phenolic cellulose paper reinforced laminated sheets, high electrical grade, copper-clad

[View on Information Provider website](#)

Abbreviation

IEC 61249-2-2:2005

Valid from

20/01/2005

Information provider

International Electrotechnical Commission

Author

International Electrotechnical Commission

Information type

IEC Standard

Format

PDF

Cited By

[This resource is cited by 1 document \(show Citations\)](#)

Description

This part of IEC 61249 gives requirements for properties of phenolic cellulose paper, reinforced copper-clad laminated sheets of high electrical grade in thicknesses of 0,8 mm to 3,2 mm. This standard covers materials with different requirements on flammability and are designated according to the following: Material 61249-2-2-1; Material 61249-2-2-2; and Material 61249-2-2-3.

For assistance with locating previous versions, please contact the information provider.

[View on Information Provider website](#)

For assistance with locating previous versions, please contact the information provider.

This resource is cited by:

IEC 61249-2-2:2005 Materials for printed boards and other interconnecting structures - Part 2-2: Reinforced base materials, clad and unclad - Phenolic cellulose paper reinforced laminated sheets, high electrical grade, copper-clad

This document is CITED BY:

- [BS EN 115-1:2008](#)

IEC 61249-2-2:2005 is cited by BS EN 115-1:2008 Safety of escalators and moving walks Part 1: Construction and installation

Back

IEC 61249-2-2:2005 Materials for printed boards and other interconnecting structures - Part 2-2: Reinforced base materials, clad and unclad - Phenolic cellulose paper reinforced laminated sheets, high electrical grade, copper-clad

Show what documents this resource is CITED BY

Show what documents this resource CITES

Description

This part of IEC 61249 gives requirements for properties of phenolic cellulose paper, reinforced copper-clad laminated sheets of high electrical grade in thicknesses of 0,8 mm to 3,2 mm. This standard covers materials with different requirements on flammability and are designated according to the following: Material 61249-2-2-1; Material 61249-2-2-2; and Material 61249-2-2-3.

[View on Information Provider website](#)

[IEC 61249-2-2:2005 Materials for printed boards and other interconnecting structures - Part 2-2: Reinforced base materials, clad and unclad - Phenolic cellulose paper reinforced laminated sheets, high electrical grade, copper-clad](#)

Description

This part of IEC 61249 gives requirements for properties of phenolic cellulose paper, reinforced copper-clad laminated sheets of high electrical grade in thicknesses of 0,8 mm to 3,2 mm. This standard covers materials with different requirements on flammability and are designated according to the following: Material 61249-2-2-1; Material 61249-2-2-2; and Material 61249-2-2-3.

[View on Information Provider website](#)

This resource does not cite any other resources.

IEC 61249-2-2:2005 Materials for printed boards and other interconnecting structures - Part 2-2: Reinforced base materials, clad and unclad - Phenolic cellulose paper reinforced laminated sheets, high electrical grade, copper-clad

This resource does not CITE any other resources.

Back

Close

Table of Contents

Print [Save](#) Email

[Feedback](#)

- [Contact us](#)

- [Privacy policy](#)
- [Disclaimer](#)
- [Copyright](#)

[Feedback](#)